

TECHNICAL DATASHEET

NITROCELLULOSE PAINT **(Gloss, semi-gloss and matte)**

PRODUCT DESCRIPTION

High performance paint based on nitrocellulose for wood and metal surfaces. It is a fast drying topcoat with good coverage exhibiting exceptional holdout, excellent color retention and overall resistance.

PRODUCT BENEFITS

- 1- Fast drying
- 2- High gloss
- 3- Good scratching resistance
- 4- Excellent durability and washability
- 5- Perfect adhesion
- 6- Good hardness
- 7- Excellent color retention

RECOMMENDED USES

A topcoat for wood, steel surfaces and automotive applications.

It can be overcoated with N.C. Lacquer to increase the gloss and for further protection and resistance.

Ideal for use on furniture, vehicle chassis and under body components, engine parts, metal fireplaces, security gates...

SURFACE PREPARATION

Surfaces should be solid, clean and dry, free from oil, grease, salt, dust and other contaminants.

- 1- Alkaline and acid surfaces should be cleaned and neutralized.
- 2- Deteriorated previous coatings, weak and blistered paints or chalky substances should be removed by scrapers, paint removers or flame spraying.
- 3- Non-disintegrated paints or glossy surfaces of previous coatings should be roughened slightly with sand paper to ensure good adhesion.

Fill all the pores and holes with NC Ready Putty to smooth the surfaces before Priming.

PHYSICAL AND CHEMICAL PROPERTIES

Physical Properties

Physical state Viscous liquid

Appearance Matte, semi-gloss, gloss

Color Range Cf. catalogue

Specific Gravity, ISO 2811 1.1- 1.3 g/cm³

Viscosity, ISO 2884 50- 70 poises

Drying Time, ASTM D5894 1-2 hours

Recoat Time 2-3 hours

Sag Resistance, ASTM D3730 Excellent

Leveling, ASTM D2801 Excellent

Scratching Resistance, ASTM D3003 Excellent

Coverage: 45-50m² /US. Gallon

Chemical Properties

Solids by Weight 50- 55 %

Solids by Volume 40- 47%

PRIMING/ THINNING/ APPLYING

Fill existing pores and holes with NC Putty.

Apply one coat of NC Primer with a dilution according to the surface condition.

After complete drying of the primer, apply NC Paint. Thin with NC Thinner in order to obtain the adequate viscosity for application.

Brush, Roller or Spray

Apply several coats if needed.

Clean tools and equipment with NC thinner immediately after use.

PACKING

In cylindrical tin containers of the following capacities:

- 1 US Quart = 0.95 L.
- 1 US gallon = 3.78 L.
- 1 Pail (5 U.S.G.) = 20 L

STORAGE

Avoid frost & excessive heat

The technical information contained in this Technical Data Sheet is to be understood as advice only and not binding in any respect.

All details about working with our products should be adapted to prevailing local conditions and materials used.