

TECHNICAL DATASHEET

CLEARCOAT 2K HS

PRODUCT DESCRIPTION

High gloss clear clearcoat providing excellent gloss, aesthetic and durable finish. The versatility of this product enables its application in either two or three coats. Its formulation boosted with high performance UV-absorbers renders a finish resistant to sunlight, yellowing and various weathering conditions.

PRODUCT CHARACTERISTICS


- 1- Good exterior durability
- 2- Remarkable weather & abrasion resistance in urban & aggressive environments
- 3- Good U.V resistance and non-yellowing properties
- 4- Good adhesion
- 5- Great gloss retention
- 6- High end hardness

RECOMMENDED USES

It is designed for use on basecoats in order to protect the coating system and give a glossy finish. It provides a great balance between hardness and overall resistance.

SURFACE PREPARATION

All surfaces should be clean, dry and free from loose and flaking material, curing compounds, dirt, oil and grease.




TECHNICAL CHARACTERISTICS

Color: clear

Density: 0.98- 1 Kg/l

Solids content: 50-55%

Spreading rate: 8-9 m²/L at a film thickness of 50 microns.




Mixing Ratio: 2:1 (Base : Catalyst)

Thinning: use thinner 2K to reach optimal spraying viscosity (up to 25%)

Hardeners:

- Hardener Slow
- Hardener Medium
- Hardener Fast



Spraying Viscosity: 18 - 20 seconds ISO 4 cups @ 25°C



Pot life: 2-4 hours at 25°C depending on the hardener used

Shelf Life: 36 months in unopened container



Number of spray coats: 2 -3 coats

Film thickness: 50- 60 microns



Drying time: @ 25°C

@ 60°C

Dust-free 30min-1 hour (depending on the catalyst used)


Ready for assembly after 5 hours

Fully cured after 24 hours

15-30 min



Recoating: After full curing or after the specified drying times + cooling.



HVLP gravity-feed spraygun

Airless

Suction feed

Gravity feed

Nozzle diameter (mm)

1.3- 1.5

0.007-0.009

1.4- 1.6

1.3-1.5

Spraying pressure

160-200 bar

3.5- 4.5 bar

3.5-4.5 bar



Cleanup: Clean spray equipment as soon as possible with Thinner

CAUTION

Flammable liquid. Keep away from flame or high heat.

Avoid inhalation of spray mist and arrange for adequate spraying precautions especially in closed areas.

PACKING

In cylindrical tin containers of the following capacities:

- 1 Quart = 0.946 L
- 1 US gallon = 3.78 L

Each container is supplied with its appropriate hardener.

STORAGE

Avoid frost & excessive heat.

SAFETY AND HANDLING

For safety precautions, please refer to Material Safety Data sheet and wear personal protective equipment when using this product.

The technical information contained in this Technical Data Sheet is to be understood as advice only and not binding in any respect.

All details about working with our products should be adapted to prevailing local conditions and materials used.