

## TECHNICAL DATASHEET

# CLEARCOAT 2K MS

### PRODUCT DESCRIPTION

2K clearcoat providing smooth and glossy finish. It has outstanding adhesion on basecoats and exhibits high protection and resistance properties.

### PRODUCT CHARACTERISTICS

- 1- Excellent adhesion
- 2- High durability
- 3- Good weathering resistance
- 4- High hardness


### RECOMMENDED USES

On basecoats in order to protect the coating system and give a glossy finish.

It provides aesthetic appearance as well as a protective clear finish.

### SURFACE PREPARATION

All surfaces should be clean, dry and free from loose and flaking material, curing compounds, dirt, oil and grease.




### TECHNICAL CHARACTERISTICS

**Color:** clear

**Density:** 1- 1.05 Kg/l

**Solids content:** 45-50%

**Spreading rate:** 7-9 m<sup>2</sup>/L at a film thickness of 50 microns.




**Mixing Ratio:** 2:1 (Base : Catalyst)

**Thinning:** use thinner 2K to reach optimal spraying viscosity (up to 10%)

## Hardeners:

- Hardener Slow
- Hardener Medium
- Hardener Fast



**Spraying Viscosity:** 18 - 20 seconds ISO 4 cups @ 25°C



**Pot life:** 2-4 hours at 25°C depending on the hardener used

**Shelf Life:** 36 months in unopened container



**Number of spray coats:** 3 coats

**Film thickness:** 50- 60 microns



**Drying time:** @ 25°C

@60°C

Dust-free 30min-1 hour (depending on the catalyst used)


Ready for assembly after 5 hours

Fully cured after 24 hours

15-30 min



**Recoating:** After full curing or after the specified drying times + cooling.



**HVLV gravity-feed spraygun**

**HE**

**Suction feed**

**Gravity feed**

**Nozzle diameter (mm)**

1.3- 1.5

1.2-1.4

1.4- 1.6

1.3-1.5

**Spraying pressure**

3.5- 4.5 bar

3.5-4.5 bar



**Cleanup:** Clean spray equipment as soon as possible with Thinner

## CAUTION

Flammable liquid. Keep away from flame or high heat.

Avoid inhalation of spray mist and arrange for adequate spraying precautions especially in closed areas.

## PACKING

In cylindrical tin containers of the following capacities:

- 1 Quart = 0.946 L
- 1 US gallon = 3.78 L

Each container is supplied with its appropriate hardener.

## STORAGE

Avoid frost & excessive heat.

## SAFETY AND HANDLING

For safety precautions, please refer to Material Safety Data sheet and wear personal protective equipment when using this product.

The technical information contained in this Technical Data Sheet is to be understood as advice only and not binding in any respect.

All details about working with our products should be adapted to prevailing local conditions and materials used.