

TECHNICAL DATASHEET

CLEARCOAT 2K Matt

PRODUCT DESCRIPTION

Clearcoat 2K Matt Clear providing matt, aesthetic and durable finish. The versatility of this product enables its application in either one or two coats. Its formulation boosted with high performance UV-absorbers renders a finish resistant to sunlight, yellowing and various weathering conditions.

PRODUCT BENEFITS


- 1- Excellent exterior durability
- 2- Remarkable weather & abrasion resistance in urban & aggressive environments
- 3- Outstanding U.V resistance and non-yellowing properties
- 4- Good adhesion
- 5- Excellent mechanical and high chemical resistance
- 6- High end hardness

RECOMMENDED USES

It is designed for use on basecoats in order to protect the coating system and give a matte finish. It provides chemical, mechanical and weathering resistance to the paint system.

SURFACE PREPARATION

All surfaces should be clean, dry and free from loose and flaking material, curing compounds, dirt, oil and grease.




TECHNICAL CHARACTERISTICS

Color: clear .

Density: 1.05- 1.1 Kg/l

Solids content: 55- 60%

Spreading rate: 8-10 m²/L at a film thickness of 50 microns.



Mixing Ratio: 2:1 (Base:Catalyst)

Thinning: use thinner 2K to reach optimal spraying viscosity (20- 30%)



Spraying Viscosity: 20 to 25 seconds ISO 4 cups @ 25°C



Pot life: 1-3 hours at 25°C depending on the hardener used.
Shelf Life: 36 months in unopened container




Number of spray coats: 1 or 2
Film thickness: 50- 60 microns



Drying time: @ 25°C Dust-free 30min-1 hour (depending on the catalyst used)
Ready for assembly after 5 hours
Fully cured after 24 hours
@ 60°C 15-30 min



Recoating: After full curing or after the specified drying times + cooling.



HVLP gravity-feed spraygun	1.3- 1.5	0.7 bar at the nozzle
Compliance gravity-feed spraygun	1.3- 1.4	2.0- 2.5 bar



Cleanup: Clean spray equipment as soon as possible with Thinner

CAUTION

Flammable liquid. Keep away from flame or high heat.

Avoid inhalation of spray mist and arrange for adequate spraying precautions especially in closed areas.

PACKING

In cylindrical tin containers of the following capacities:

- 1 Quart = 0.946 L
- 1 US gallon = 3.78 L.

Each container is supplied with its appropriate hardener.

STORAGE

Avoid frost & excessive heat.

SAFETY AND HANDLING

For safety precautions, please refer to Material Safety Data sheet and wear personal protective equipment when using this product.

The technical information contained in this Technical Data Sheet is to be understood as advice only and not binding in any respect.

All details about working with our products should be adapted to prevailing local conditions and materials used.